



Formulation Additives by NAC Revision 4: October, 2023

NACO-DS 1040

Wetting and Dispersing Additive (Solvent Based)

Polymeric wetting and dispersing additive for solvent-borne and solvent-free coating systems for stabilizing inorganic pigments, in particular titanium dioxide. suitable for high gloss solvent-based systems with broad compatibility in a wide range of resins. Suitable for many coating systems such as automotive refinish and OEM coatings, solvent-based industrial coatings, coil coatings, especially TiO₂.

(10 min., 150 °C):

Product Data

Composition:

Copolymer with acidic groups

Typical Properties:

Note: This information is intended as a guideline only and should not be used to issue specifications. Slight deviations do not affect application and capability of the product.

Physical Form:	Clear light yellow liquid
Active Content:	52%
Density (20 °C):	0.95-1.00 g/ml
Acid Value:	35-45 mg KOH/g
Non-volatile matter	

52%

Applications

Applications > Recommended for > Particularly Recommended:

Coatings > Solvent based systems > Polyester and Alkyd systems

Recommended Levels:

Note: The properties and performance of the additive are greatly dependent upon the specific formulation in which it is utilized and, consequently, should always be tested (possibly at different treatment levels, temperatures, and/or time intervals) to verify performance before use.

Based on

Total formulation weight:	0.5%
Titanium dioxide:	2-4%
Organic pigments:	6-8%
Carbon black:	8-10%

Special Feature:

Suitable for high gloss solvent-based systems

Incorporation and Processing Instructions:

For optimum performance, the additive must be incorporated into the mill base before the addition of pigments.

Storage and Transportation:

Separation or turbidity may occur at low temperatures. Heat to 30-40 °C and stir. The minimum shelf life in closed containers is 12 months from the date of manufacture.

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

Tel: (+9821) 44787098 Email: info@noyanafzon.com WhatsApp: (+98) 9056030635